

SECURITY CONTRACTOR SERVICES

Large Enough To Serve Small Enough To Care

Poly(Vinyl Chloride) (PVC)- Coated Steel Chain Link Fence Fabric Class 2a - Extruded and Adhered ASTM F668, Federal specification RR-191 Type IV, AASHTO M-181 Type IV

1. PRODUCT NAME

Extruded and Adhered Poly(Vinyl Chloride)-PVC Coated Steel Chain Link Fence Fabric

2. DISTRIBUTOR

Corporate Headquarters: 5339 Jackson St, North Highlands, CA 95660

Phone:(916)338-4800

SCS centers are located throughout the West Coast of the United States

3. PRODUCT DESCRIPTION

Basic Use: Extruded and adhered fabric is a boned vinyl, high strength galvanized steel chain link fence fabric for industrial, commercial, and institutional applications. Extruded and adhered fabric is contained in local, state and federal government specifications for use in prison, road, dock, airport, housing, forestry, and military use.

Composition and Materials: The galvanized steel core wire for producing extruded and adhered PVC coated steel chain link fence fabric is produced by cold-drawing good commercial grade steel rod into wire of the appropriate diameter. The steel rod from which the wire is drawn is produced by the open heart, electric furnace or basic oxygen process. The galvanized coating is produced by passing the cleaned wire through a bath of molten zinc which conforms to ASTM B6. The extruded and adhered PVC coating is produced by first applying a molecular bonding agent to the galvanized core wire to eliminate slippage of the PVC. A coating of PVC up to 0.025 in. (0.64 mm) is then pressure bonded to the wire.

Standards:

- ASTM B 6 Slab Zinc
- ASTM F567 Installation of Chain Link Fence
- ASTM F668 Poly (Vinyl Chloride) (PVC) and Other Organic Polymer-Coated Steel Chain Link Fence Fabric, Class 2b
- Federal specification RR-F-191K/1D Fencing, Wire and Post Metal (Chain-Link Fence Fabric), Type IV
- American Association of State Highway Transportation Officials (AASHTO) M-181 Chain Link Fence, Type IV, Class A

4. TECHNICAL DATA

General: The manufacturer, if requested, will supply samples and certification that all materials furnished fully comply with the appropriate specifications.

Chain Link Fence Fabric: The base metal of the chain link fence fabric is composed of commercial quality, medium-carbon galvanized (zinc coated) steel wire. The vinyl coating is continuously applied over the galvanized wire by the extrusion process. A bonding pressure to 5 ksi (34 MPa) ensures a dense and impervious coating free of voids, as well as a smooth lustrous surface appearance. Vinyl coating thickness, galvanized coating weight, and wire tensile strength conform to ASTM F668, Class 1, Federal specification RR-F-191 Type IV, and AASHTO M-181 TypeIV, Class A, as shown in Table 1. The wire is PVC coated before weaving and is free and flexible at all joints. Unless otherwise specified, fabric woven in 2 in (50mm) mesh, under 72" (1,830 mm) in height, is knuckled at both selvages: fabric 72" (1,830 mm) high and over is knuckled at one selvage and twisted at the other. All fabrics woven into meshes under 2 in (50) have both selvages knuckle. See Table 2.

Wire Coating: Only plasticized poly (vinyl chloride) (PVC) with low temperature (-20 C; -4 F) plasticizer and no extenders or extraneous matter other than the necessary stabilizers and pigments, is used. The PVC coating resists attack from prolonged exposure to dilute solutions of most common mineral acids, seawater, and dilute solutions of most salts and akali. See Table 3.

ASTM Color System: Standard colors conform to ASTM F934 and include:

Dark		
Green	Brown	Black
28.61	27.76	22.30
-12.59	3.37	-0.09
1.95	4.28	-0.85
	Green 28.61 -12.59	Green Brown 28.61 27.76 -12.59 3.37

Other colors are available by special order.

Coating Adhesion: The PVC coated wire shall pass the test for adhesion contained in ASTM F668 for Class 2a chain link fabric.

5. INSTALLATION

Install fence in accordance with ASTM Practice 567. Handle all PVC coated material with care. If PVC coating is damaged during installation, the contractor must replace or repair the material at own expense.

6. AVAILABILITY AND COST

Availability: PVC-coated steel chain link fence fabric is available for shipment throughout the United States and worldwide.

Cost: Material cost may vary depending on specific requirements. Costs may be obtained through all SCS Service Centers.

7. WARRANTY

Extruded PVC coated steel chain link fence fabric is warranted for 20 years against failure due to rust or corrosion.

8. MAINTENANCE

Periodic inspection is recommended but no routine maintenance is required.

9. TECHNICAL SERVICES

Technical services are available through the SCS Corporate Office:

Phone: (916)338-4200 Fax: (916)338- 1140 Quote: (800)843-7893

Poly (Vinyl Chloride) (PVC) - Coated Steel Chain Link Fence Fabric Extruded and Adhered ASTM F668 Class 2a, Federal specification RR-F-191 Type IV, AASHTO M-181 Type IV, Class B

Table 1 - PVC-Coated Steel Wire Characteristics

Zinc Co	ated Core Wi	re Sizes	PVC Coated Finished Wire Size	PVC Coa	ted Wire Variance	Core Wire 2 Weigh	Zinc Coating it, min.	PVC Coatin	g Thickness	_	Strength, mum	Tensile Str	ength min
GA	inch	mm	ga	inch	mm	oz/ft	g/m	inch	mm	lbf	N	ksi	Mpa
9	0.148	3.76	6	0.005	0.13	0.3	92	0.015 to		1,290	5,740	75	515
11	0.12	3.05	8	0.005	0.13	0.3	92	0.015 to	0.38 to 0.64	850	3,780	75	515
14	0.08	2.03	11	0.005	0.13	0.25	76	0.025		380	1,690	75	515

Table 2 - PVC Coated Chain Link Fabric Sizes

Mash Size		Finished Wire Gage	Fabric Wire Height Inch (mm)	Selvage K-Knuckled, T- Twisted/Barbed	Roll Size		
inch	mm	wife Gage	(111111)	i wisteu/ barbeu	ft	m	
2"	50	6, 8	36-240 (910-6,100)	KK, KT, TT	50	15.24	
1-3/4"	44	6, 8	36-240 (910-6,100)	KK Only	25	7.62	
1"	25	8	36-144 (910-3,660)	KK Only	25	7.62	

Maximum Security Mesh

5/8"	16	11	36-72 (910-1,830)	KK Only	25	7.62
1/2"	13	11	36-72 (910-1,830)	KK Only	25	7.62
3/8"	10	11	36-72 (910-1,830)	KK Only	25	7.62

Table 3: Typical Vinyl Properties

Test	Test Method	Value
Specific Gravity	ASTM D 792	1.30 +/- 0.03
Hardness, Durometer	ASTM D 2240	A90 +/- 5
Tensile Strength	ASTM D 412	2,600 +/- 5%
Ultimate Elongation	ASTM D 412	275% +/- 5%
Mandrel Bend Test, 10X mandrel	ASTM F 668	-20 degrees F
Dielectric, Strength, volt/mil	ASTM D 149	750
Compression cut-through, lbs	Bell Labs	1,500
Accelerated Aging Test	ASTM D 1499	1500 hrs. @145F